



Triton Hydrolock

BBA certified, fully bonded type A waterproofing barrier.

Description

A mechanically bonded Geosynthetic Clay Liner (GCL) composite of pulverised bentonite embedded between two layers of geotextile. The internal 5kg of natural sodium bentonite swells in contact with water to form a low permeability waterproofing barrier.

Triton Hydrolock when used with properly designed concrete, is satisfactory for use as a fully bonded Type A waterproofing protection as defined in BS 8102: 2022 for the waterproofing of new structures. Triton Hydrolock can be used externally on concrete to provide an effective barrier to the transmission of liquid water where Grades 1 to 3 waterproofing protection are required as defined in table 2 of BS 8102: 2022.

Technical Data

Characteristics	Test Method	Unit	Hydrolock
Geotextile Layers			
Carrier Layer (PP Woven) MPUA	EN ISO 9864	g/m ²	100
Cover Layer (PP Non-woven) MPUA	EN ISO 9864	g/m ²	200
Bentonite (Sodium Bentonite) Layer			
Montmorillonite Content	CUR 33 (VDG 69)	%	>75
Swell Index	ASTM D 5890	ml/2g	≥24
Fluid Loss	ASTM D 5891	ml	<18
Moisture Content	DIN 18121-1	%	<12
Water Absorption	DIN 18132	%	>500
Geosynthetic Clay Liner			
Mass per unit area of Bentonite	EN 14196	g/m ²	5000
Mass per unit area of GCL	EN 14196	g/m ²	5300
Tensile Strength (MD/CMD)	EN ISO 10319	kN/m	10.5/8.5
Permeability	ASTM D 5887	m/s	≤3.5 x 10 ⁻¹¹
Index Flux	ASTM D 5887	m ³ /m ² /s	≤5.0 x 10 ⁻⁹
Grab Tensile Strength	ASTM 4632	N	>400
CBR puncture Resistance	EN ISO 12236	kN	>1.8
Peel Strength	ASTM D 6496	N/10cm	>60
Peel adhesion to concrete	ASTM D 903 (mod)	kN/m	5.3
Roll Dimensions			
Roll Width x Length	Typical	m	1.15 x 5.1
Roll Area	Typical	m ²	5.865
Rolls Per Full Pallet	-	-	32

*Data provided are average values derived from standard tests and are subject to usual product variation. The right is reserved to make changes without notice at any time.

Handling

Roll weights can be in excess of 20kg and hence appropriate care and equipment is required for unloading and handling.

Storage

Rolls of Triton Hydrolock should be stored on stable/level ground and stacked not more than five rolls high, with no other material stacked on top. The rolls can be stores outdoors when packaged but should be protected from exposure to UV.

Installation

Triton Hydrolock should be installed in accordance with the product installation guidelines available on request.

Triton Contact Details:

Triton Systems
Units 3 – 5 Crayford Commercial Centre, Greyhound Way, Crayford, Kent DA1 4HF

Tel: 01322 318 830

Fax: 01322 524 017

Email: info@tritonsystems.co.uk

www.tritonsystems.co.uk